









VIASOL *ELASTIC comfort*


High elastic polyurethane coating system, with impact sound reducing rubber or foam mat, gentle to joints, temperature pleasing to the feet, with good mechanical and chemical properties and a wide colour spectrum.

SYSTEM BUILD-UP

-  Coloured seal coat:
VIASOL PU-S6000P
-  Self-levelling coating
VIASOL PU-C525
-  Levelling coating (recommended)
VIASOL PU-C525
-  Pore sealer:
VIASOL PU-L375
-  Elastic mat 4 – 6 mm
with adhesive: VIASOL PU-B976
-  Levelling coating (optional)
VIASOL PU-C525
-  Primer for cementitious substrates:
VIASOL EP-T703 or other
-  Substrate: concrete, cementitious screed,
asphalt, wood and others

SYSTEM THICKNESS

6.0 – 11.0 mm



SYSTEM HIGHLIGHTS

- Many colours available
- Certified slip resistance
- Impact sound reduction
- Low emission tested accord. AgBB guidelines and other European standards
- TÜV-ProfiCert Premium certified

APPLICATION FIELDS

- Schools, kindergarten, universities
- Hospitals, nursing and residential homes
- Offices and public buildings
- Restaurants and canteens
- Shops, foyers and exhibition areas



SYSTEM BENEFITS

- Impact sound reducing up to 20 dB
- Gentle to knees and joints, durable elasticity
- Low emission accord. to AgBB guidelines and other European standards
- Self-leveling, seamless and joint less
- High abrasion resistance, suitable for chairs with wheels
- Good chemical resistance
- Homogeneous and anti-skid surface
- Hygienic, no pores, impermeable to liquids
- Easy to clean and maintain
- Available in many colours
- Very high color and UV-stability
- Suitable for floor heating

Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str.78, D-72108 Rottenburg,
Page 1/2 version no. 5

Tel: +49/7472-94999-0, info@viacor.de, www.viacor.de
issue: 10-2019

VIASOL system data sheet

GREEN LINE ECO

VIASOL *ELASTIC comfort*

APPLICATION AND CONSUMPTION

| layer | product | consumption (kg/m ²) | sand broadcasting (kg/m ²) | thickness mm | application |
|--------------------------------------|--|----------------------------------|--|--------------|---|
| Seal coat, flexible, coloured | VIASOL PU-S6000P | 0.10 – 0.13 | none | 0.08 – 0.10 | roller or rubber squeegee and roller |
| Self-levelling coating, high elastic | VIASOL PU-C525 | 2.0 – 3.0 | none | 1.5 – 2.2 | notched trowel |
| Levelling layer, (recommended) | VIASOL PU-C525 | 0.6 – 1.0 | none | approx. 0.5 | notched trowel |
| Pore sealer | VIASOL PU-L375 | ca. 1,0 | none | 0.1 – 0.2 | rubber squeegee or trowel |
| elastic mat, adhesive | foam mat VIASOL PU-B976 | 4.0 – 6.0 mm ca. 0.8 | none | 4.0 – 6.0 | roll out on fresh adhesive notched trowel |
| Levelling layer, (optional) | VIASOL PU-C525 | 0.6 – 1.0 | none | approx. 0.5 | notched trowel |
| Primer | VIASOL EP-T703 or others | ca. 0.4 | QS 0.3 – 0.8 mm approx 0.5 | ca. 0.3 | roller or rubber squeegee |
| Substrate | Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength ≥ 1.5 N/mm ² , residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with VIASOL quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data. | | | | |
| Note | Detailed application instructions are available upon request or refer to the technical product data sheet. | | | | |

TECHNICAL DATA

| Property | standard | result |
|-----------------------------------|---------------------------|---|
| Tensile strength(top coating) | DIN 53504 | approx.9 N/mm ² |
| Elongation at break (top coating) | DIN 53504 | approx. 200 % |
| Tear resistance | DIN 53515 | approx. 15 N/mm ² |
| Shore-Hardness | DIN ISO 868 | 75 A after 28 d |
| Way of use | In relation to DIN EN 685 | Private buildings: 23 Public buildings: 34 |
| Noise reduction | DIN 4109 | ca. 12 – 20 dB |
| Impact strength | DIN EN 13813 | ≥ 4 Nm (IR4) |
| Wear resistance (Taber) | ISO 9352, ASTM D 1044 | ≤ 80 mg |
| Anti-skid properties | BGR 181 / DIN 51130 | class R9 / R10 |
| Adhesive strength | DIN ISO 4624 | >1.5 N/mm ² |
| Fire behaviour system | EN 13501-1 | NPD |

Remark: For further information, please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all VIACOR data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.viacor.de or contact us directly)– all technical information is subject to change without prior notice.

Manufacturer:

VIACOR Polymer GmbH, Graf-Bentzel-Str.78, D-72108 Rottenburg,
Page 2/2

Tel: +49/7472-94999-0, info@viacor.de, www.viacor.de
issue: 10-2019